

## Calibration of Gold

Sr. No	Time (sec)	Thickness #1 (nm)	Thickness #2 (nm)	Thickness #3 (nm)	Thickness #4 (nm)	Thickness #5 (nm)	Avg Thickness (nm)
1	0	0	0	0	0	0	0
2	90	25.47	25.74	25.4	23.45	26.7	25.352
3	113	32.29	31.88	32.17	32.7	34.97	32.802
4	135	35.54	35.05	36.48	34.49	36.6	35.632
5	180	50.39	49.65	50.71	51.68	50.33	50.552

